


WGI, II, III WET FILM THICKNESS GAUGE

SP4000, SP4010, SP4020, SP4050

DATASHEET

PRODUCT DESCRIPTION

Hexagonal/Octagonal precision measuring comb made of heavy stainless steel. The high-grade stainless steel will not be affected by acid or base elements. Available in Microns and Mils scale.

**BUSINESS**

Automotive, coating industry, construction/building maintenance, galvanize, laboratory, paint, shipping industry, steel protection, wholesale, wood

STANDARDS

ISO 2808, JIS Z2371

ORDERING INFORMATION

SP4000 - WGI wet film thickness comb 20-370 μm
SP4010 - WGII wet film thickness comb 25-2000 μm
SP4020 - WGIII wet film thickness comb 50-10000 μm
SP4050 - WGII wet film thickness comb 1-80 mils

SPECIFICATIONS

4 models available for several different applications:

- WG-I 20-370 μm in 24 steps (6x4) for decorative paints and primers.
- WG-II 25-2000 μm in 36 steps (6x6) With edge radius check (2mm) for protective coatings and high solids. With edge grinding check (2mm)
- WG-III 50-10000 μm in 71 steps (8x9) Scale division: 0-900:50 μm , 900-5500:100 μm , 5500-9000:500 μm for extremely thick films such as floor coatings, fillers, fire proofing, plaster, adhesives etc.
- WG-II 1-80 mils in 36 steps (6x6) With edge radius check (2mm) for protective coatings and high solids. With edge grinding check (2mm)

SPECIAL CARE

- Always clean the instrument after use.
- Clean the instrument using a soft dry cloth. Never clean the instrument by any mechanical means such as a wire brush or abrasive paper. This may cause, just like the use of aggressive cleaning agents, permanent damage.
- Always keep the instrument in its pouch when not in use.

DISCLAIMER

The right of technical modifications is reserved.

The information given in this sheet is not intended to be exhaustive and any person using the product for any purpose other than that specifically recommended in this sheet without first obtaining written confirmation from us as to the suitability of the product for the intended purpose does so at his own risk. Whilst we endeavour to ensure that all advice we give about the product (whether in this sheet or otherwise) is correct we have no control over either the quality or condition of the product or the many factors affecting the use and application of the product. Therefore, unless we specifically agree in writing to do so, we do not accept any liability whatsoever or howsoever arising for the performance of the product or for any loss or damage (other than death or personal injury resulting from our negligence) arising out of the use of the product. The information contained in this sheet is liable to modification from time to time in the light of experience and our policy of continuous product development.